



Milford Corporate Center
77 Milford Drive, Suite 258
Hudson Ohio 44236
330-653-9104

Current Issue Date:
November, 2011
Version Number 1

Product Data Sheet

MTK-350 Alkyl Phenolic Resin

MTK-350 is a non-heat reactive alkyl phenolic tackifying resin that is used to improve the tack for natural and synthetic rubber compounds. Reztac 100 is recommended for use in tires, conveyor belts and hoses.

Physical Properties

Specifications

Softening Point, °C
2°C/Min.↑

86~100

Specific Gravity @ 25° C

1.00~1.06

Ash (%)

Max. 0.2

Appearance: Dark yellowish pastille

Package: 25kg poly bags, super sacks, bulk

We believe the information contained in this document is reliable. However, this does not release our customers from the obligation to test the products supplied by us as to their suitability for intended process and end use. Since many of the applications, uses, and processing of the products are beyond our control, we cannot be held liable for any consequential service failures that occur.