



56 Milford Drive, Suite 100  
Hudson Ohio 44236  
330-653-9104

Current Issue Date:  
October, 2018  
Version Number 1

## Product Data Sheet

### Rezwax™ 65

Rezwax 65 is a fully refined paraffin & microcrystalline wax blend that is derived from petroleum. It is comprised of 60% paraffin and 40% microcrystalline. Rezwax 65 has excellent resistance to most alkalis and acids. It is white in color and has low odor, which makes it suitable for many applications. In addition to its many suitable applications, Rezwax 65 is highly recommended for rubber applications.

#### Physical Properties

#### Typical Properties

Congealing Point (°C) (DIN ISO 2207)	68
Needle Penetration (25°C mm/10) (DIN 51 579)	17
Viscosity (100°C mm <sup>2</sup> /s) (DIN EN ISO 3104)	8.5
Oil Content (Mass.-%) (DIN 51531)	0.6
Color	1.0
Appearance	Granular

Package: 25kg bags, super sacks, bulk

Due to chemical structure and composition, granulated and flaked resins may be subject to clumping, blocking and/or fusing. The previously mentioned matters can be accelerated if materials are subjected to any or all of the following conditions: 1) storage of material is prolonged; 2) material is above the ambient temperature; 3) material is exposed to pressure, i.e. stacking pallets, or a compounding of the previously listed conditions.

In order to preserve the composition of the material, it is recommended to: 1) avoid prolonged storage of the material; 2) store the material in a temperature-controlled area; 3) use caution when stacking or applying pressure to the material.

Note: clumping, blocking, and/or fusing does not have negative effects on the material specifications.

We believe the information contained in this document is reliable. However, this does not release our customers from the obligation to test the products supplied by us as to their suitability for intended process and end use. Since many of the applications, uses, and processing of the products are beyond our control, we cannot be held liable for any consequential service failures that occur.